

## LOW VISCOSITY PROTECTIVE OIL

### H-150

No.	Test Description	Standard/Method	Typical value	Unite	Remark
1	Appearance	—	Bright		
2	Density @ 15 °c	A.S.T.M D 4052	0.85	gr/cm <sup>3</sup>	
3	Viscosity @ 20 °c	A.S.T.M D 445	15.2	C.S.T	
4	Viscosity @ 40 °c	A.S.T.M D 445	7.5	C.S.T	
5	Flash point C.O.C	A.S.T.M D 92	156		
6	Pour point	A.S.T.M D 97	-15	gr/cm <sup>3</sup>	
7	Sulfate ash	A.S.T.M D 482	0.30%		
8	Soaponification No.	A.S.T.M D 94	<3	Mg koh/gr	
9	% Water	A.S.T.M D 1533	Nil		
10	Solid content	A.S.T.M D 893	Nil		
11	Rust Prevention	DIN 5138 PRT 1	Pass		
12	cleaning test	UNICHIM 445	Pass		