

**PROTECTIVE OIL
MC-300**

No.	Test Description	Standard/Method	Typical value	Unite	Remark
1	Appearance	—	Bright		Liquid
2	Color	—	Brown		
3	Density @ 15 °c	A.S.T.M D 4052	0.848	gr/cm ³	
4	Viscosity @ 40 °c	A.S.T.M D 445	18.63	C.S.T	
5	Viscosity @ 100 °c	A.S.T.M D 445	4.57	C.S.T	
6	Viscosity index	A.S.T.M D 2270	134		
7	Flash point C.O.C	A.S.T.M D 92	>170	°c	
8	Fire point C.O.C	A.S.T.M D 92	>180	°c	
9	Acid number	A.S.T.M D 974/87	<1	Mg.Koh/gr	
10	% Water	A.S.T.M D 1533	Nil		
11	Coverage	Quaker LS 950018	2	gr/cm ³	
12	Humidity cabinet	DIN 50017	Pass		
13	Cleaning test	UNICHIM 445	Pass		
14	Stack stain		Pass		

طریقه استفاده به 4 روش ذیل

- 1- بروشینگ
- 2- الکتواستاتیک
- 3- اسپری کردن
- 4- غوطه وری